



BY SWISS KRONO GROUP

DYNAMIC 2

LAMINATE FLOORING



www.blauer-engel.de/uz176



1380 x 193 x 8 mm / 54.33 x 7.59 x 0.314"



ABRASION CLASS
COMMERCIAL 32 / AC 4

Web: fixitdesign.ae
Phone: [+971554722980](tel:+971554722980)
Email: info@fixitdesign.ae





Barrow Oak – D4781





Lorine Light – D4991






Nevada Pine - D4127






Walnut Palazzo – D4757





Walnut Historia – D4773





Elbe Oak – D3901





DYNAMIC 2

LAMINATE FLOORING

TEST	CHARACTERISTICS	TEST METHOD
Formaldehyde emission	< 0.05 ppm	EN 717-1
Surface stain resistance	Grade 5, no visible changes to surface	EN 438-2.15
Lightfastness	≥ Level 6 Blue Wool Scale ≥ Level 4 Grey Scale	EN ISO 105-B02 EN 20105-A02
Resistance to cigarette embers	Grade 4, no visible changes to surface	EN 438-2.18
Fire resistance	Ignites with difficulty, at least C _{fl} -s1	EN 13501-1
Height difference between connected elements	Average: ≤ 0.10 mm max: ≤ 0.15 mm	EN 13329
Edge straightness (bend)	≤ 0.3 mm/m	EN 13329
Openings between connected elements	Average: ≤ 0.15 mm max: ≤ 0.20 mm	EN 13329
Static indentation	< 0.01 mm – no visible changes, Impression in test with straight steel cylinder of 11.3 mm diameter	EN 433

		RESISTANCE ((m ² x K) / W)	
8 mm	0.13	0.06	

LENGTH	WIDTH	PANELS PER BOX	m ² /BOX	BOXES PER PALLET	m ² / PALLET
1380 mm	193 mm	8	2.131	56	119.320



KRONOTEX

BY SWISS KRONO GROUP

