



BY SWISS KRONO GROUP



DYNAMIC 3

LAMINATE FLOORING



www.blauer-engel.de/uz176



1380 x 193 x 8 mm / 54.33 x 7.59 x 0.314"



ABRASION CLASS
COMMERCIAL 32 / AC 4

Web: fixitdesign.ae

Phone: [+971554722980](tel:+971554722980)

Email: info@fixitdesign.ae





Block Wood – D3585





Black and White – D2955






Cutter Oak - D2450





Kallisto – D4771






Stockholm Ash – D3007





Maple - D4636





DYNAMIC 3

LAMINATE FLOORING

TEST	CHARACTERISTICS	TEST METHOD
Formaldehyde emission	< 0.05 ppm	EN 717-1
Surface stain resistance	Grade 5, no visible changes to surface	EN 438-2.15
Lightfastness	≥ Level 6 Blue Wool Scale ≥ Level 4 Grey Scale	EN ISO 105-B02 EN 20105-A02
Resistance to cigarette embers	Grade 4, no visible changes to surface	EN 438-2.18
Fire resistance	Ignites with difficulty, at least C _{fl} -s1	EN 13501-1
Height difference between connected elements	Average: ≤ 0.10 mm max: ≤ 0.15 mm	EN 13329
Edge straightness (bend)	≤ 0.3 mm/m	EN 13329
Openings between connected elements	Average: ≤ 0.15 mm max: ≤ 0.20 mm	EN 13329
Static indentation	< 0.01 mm – no visible changes, Impression in test with straight steel cylinder of 11.3 mm diameter	EN 433

		RESISTANCE ((m ² x K) / W)			
8 mm	0.13	0.06			

LENGTH	WIDTH	PANELS PER BOX	m ² /BOX	BOXES PER PALLET	m ² / PALLET
1380 mm	193 mm	8	2.131	56	119.320



KRONOTEX

BY SWISS KRONO GROUP



FIXIT DESIGN
CARPET AND CURTAINS TRANDING L.L.C